

TECHNICAL DATASHEET



NC KOMBI FILLER

ART. NO: #126.052

NC Kombi Filler is a one component nitro cellulose stopper for filling small imperfections like scratches, pinholes and shallow dents. Due to its smooth consistency, Kombi Filler can be applied in very thin coats. After sanding, a porous free surface is provided which can be painted without the need of a primer.

APPLICATION

Due to its fine structure, Kombi Filler is used as a final surface filler before the paint application. Furthermore, small imperfections (scratches) and stonechip damages can be filled easily.

HANDLING

The surface must be clean, dry and grease free. Painted surfaces must be thoroughly sanded. Kombi Filler can be applied directly to a primer, provided that the primer is completely dry.

Only apply the filler in thin layers. For thicker layers apply in stages leaving approx. 30-40 minutes between applications. The filler can be wet sanded after approx. 3 hours with a fine grit abrasive paper. Then a primer coat can be applied or an acrylic or synthetic resin based lacquer is directly applied.

SAFETY

The before mentioned technical data and information, especially the recommendations for applying and using our products, are based on our current knowledge and experience when applied under normal conditions. In practice, the materials, surfaces or site conditions are so different that no warranty regarding the working results or liability, arising out of any relationship, can be inferred neither from this information nor from a verbal consultation, except we are charged with intent or gross negligence. In this case the user is obliged to prove that he has informed us about all points required for a proper and promising judgement in writing, in time and completely. Patent rights of any third party are to be observed. Furthermore, our general sales and delivery Terms and Conditions and the latest Technical Data Sheet, which should be demanded, apply.

Directions for handling and waste disposal are in our Security Safety Data Sheet and the specifications of the Employers Liability Insurance Association for the chemical industry.

PRODUCT DATA

Packaging: tubes

Colour: grey

Specific weight: 1.455 kg/l

Hardening time: approx. 3 hours

Shelf life:

min. 6 months at 18 - 20°C
(in the closed original container)